

# SPECIFICATION

## SELENMETALL

### SELENIUM METAL – SELENIUM METALLIQUE– SELENIO METALICO

99.8 % Powder 100 mesh

Selen – Selenium – Sélénium – Selenio.....	99.8 %	min.
Verunreinigungen – Impurities – Impuretés – Impurezas:		
Arsen		
Arsenic – Arsenic – Arsénico .....	50 ppm	max.
Cadmium		
Cadmium – Cadmium – Cadmio .....	5 ppm	max.
Kupfer		
Copper – Cuivre – Cobre .....	20 ppm	max.
Eisen		
Iron – Fer – Hierro .....	50 ppm	max.
Quecksilber		
Mercury – Mercure – Mercurio .....	10 ppm	max.
Nickel		
Nickel – Nickel – Niquel .....	10 ppm	max.
Blei		
Lead – Plomb – Plomo .....	20 ppm	max.
Tellur		
Tellurium – Tellure – Telurio .....	500 ppm	max.
Feuchte		
Moisture – Teneur en eau – Contenido de agua .....	0.2 %	max.
Glührückstand		
Residue of ignition – Résidue involatile – Residuo involátil.....	0.1 %	max.

Änderungen vorbehalten. - This specification may be subject to changes.

# SPECIFICATION

## SELENMETALL

### SELENIUM METAL – SELENIUM METALLIQUE – SELENIO METALICO

99.8 % Powder 100 mesh

Seite 2 – page 2 – page 2 – página 2

Typische Siebanalyse	100 % < 1.000 mm (18 mesh)
Typical sieve analysis – Granulométrie typique –	80 % < 0.300 mm (50 mesh)
Análisis de tamiz típico	50 % < 0.150 mm (100 mesh)
	30 % < 0.075 mm (200 mesh)
	20 % < 0.045 mm (325 mesh)
Schüttdichte	
Bulk density - Densité apparente – Densidad aparente	2.5 – 3.0 kg/l
Aussehen	graues Pulver
Appearance – Apparence – Apariencia	grey powder – poudre gris – polvo gris
Geruch	ohne
Odour – Odeur – Olor	none – sans – sin
Verpackung	
Packaging – Emballage – Embalaje	25 kg net steel drums with inliner
Transport	
Transportation – Transport – Transporte	not classified according to ADR

Änderungen vorbehalten. - This specification may be subject to changes.