



# SPECIFICATION

## SELENMETALL

### SELENIUM METAL – SELENIUM METALLIQUE– SELENIO METALICO

99.8 % Powder 200 mesh

Selen – Selenium – Sélénium – Selenio..... 99.8 % min.

#### Verunreinigungen – Impurities – Impuretés – Impurezas:

Arsen

Arsenic – Arsenic – Arsénico ..... 50 ppm max.

Cadmium

Cadmium – Cadmium – Cadmio ..... 5 ppm max.

Kupfer

Copper – Cuivre – Cobre ..... 20 ppm max.

Eisen

Iron – Fer – Hierro ..... 50 ppm max.

Quecksilber

Mercury – Mercure – Mercurio ..... 10 ppm max.

Nickel

Nickel – Nickel – Niquel ..... 10 ppm max.

Blei

Lead – Plomb – Plomo ..... 20 ppm max.

Tellur

Tellurium – Tellure – Telurio ..... 500 ppm max.

Feuchte

Moisture – Teneur en eau – Contenido de agua ..... 0.2 % max.

Glührückstand

Residue of ignition – Résidue involatile – Residuo involátil..... 0.1 % max.

Änderungen vorbehalten. - This specification may be subject to changes.



# SPECIFICATION

## SELENMETALL

### SELENIUM METAL – SELENIUM METALLIQUE – SELENIO METALICO

99.8 % Powder 200 mesh

Seite 2 – page 2 – page 2 – página 2

Granulometrie	100 % < 0.500 mm (35 mesh)
Granulometry – Granulométrie – Granulometria	min. 99.8 % < 0.150 mm (100 mesh)
	min. 98 % < 0.075 mm (200 mesh)
Schüttdichte	
Bulk density - Densité apparente – Densidad aparente	2.5 – 3.0 kg/l
Aussehen	graues Pulver
Appearance – Apparence – Apariencia	grey powder – poudre gris – polvo gris
Geruch	ohne
Odour – Odeur – Olor	none – sans – sin
Verpackung	
Packaging – Emballage – Embalaje	25 kg net steel drums with inliner
Transport	
Transportation – Transport – Transporte	not classified according to ADR

Änderungen vorbehalten. - This specification may be subject to changes.